



J. Šesták, University of West Bohemia, Czech Republic; J.J. Mareš and P. Hubík, Academy of Sciences of the Czech Republic, Prague, Czech Republic (Eds.)

Glassy, Amorphous and Nano-Crystalline Materials

Thermal Physics, Analysis, Structure and Properties

1st Edition, 2011, XVII, 380 p., Hardback

► 139,95 € | ► £126.00 | ► \$189.00 | ► CHF 201.00

ISBN : 978-90-481-2881-5

For more info, please go to:

<http://www.springer.com/materials/special+types/book/978-90-481-2881-5>

Glassy, Amorphous and Nano-crystalline Material: Thermal Physics, Analysis, Structure and Properties includes twenty-one chapter contributions from an international array of distinguished academics based in Asia, Australia, Eastern and Western Europe, Russia, and the USA. The book provides a coherent and authoritative overview of cuttingedge themes involving the thermal analysis, applied solid-state physics and the microcrystallinity of selected materials and their macro- and microscopic thermal properties. Selected chapters featured in the book include: Essential attributes of glassiness regarding the nature of non-crystalline solids; Aspects of vitrification, amorphization, disordering and the extent of nano-crystallinity; The basic role of thermal analysis in polymer physics; Classical and quantum diffusion and their application to the self-organized oscillatory reactions; Specificity of low temperature measurements applied to nano-crystalline diamante; Thermophysical properties of natural glasses at the extremes of the thermal history profile; Phenomenological meaning of temperature as background for the history and development of thermal analysis and calorimetry. Advanced undergraduates, postgraduates and researchers working in the field of thermal analysis and calorimetry will find this contributed volume invaluable.

- Treats different aspects of thermal properties of glassy and amorphous structures in a complex and comprehensive way
- A collection of works written by a range of internationally recognized scientists
- A monograph written both for students and researchers

Order Now!

Yes, please send me _____ copies

Glassy, Amorphous and Nano-Crystalline Materials
ISBN 978-90-481-2881-5

Methods of Payment Check/Money Order enclosed AmEx MasterCard VISA

Card No.

Exp. Date

Please send orders to:

Outside the Americas:

Springer
Order Department
PO Box 2485
Secaucus, NJ 07096-2485
USA

Springer
Customer Service Center GmbH
Haberstrasse 7
69126 Heidelberg
Germany

- Call toll-free 1-800-SPRINGER
8:30 am – 5:30 pm ET
- Fax your order to (201) 348-4505
- Web springer.com
- Email orders-ny@springer.com

- Call: + 49 (0) 6221-345-4301
- Fax: + 49 (0) 6221-345-4229
- Web: springer.com
- Email: orders-hd-individuals@springer.com

Name
Address
Street Address
(Sorry, we cannot deliver to P.O. boxes)
City / State / ZIP-Code
Country
Telephone / Email
Date ✕
Signature ✕

CA, MA, NJ, NY, and PA residents, please add sales tax. Canadian residents, please add 5% GST. Please add \$5.00 for shipping one book and \$1.00 for each additional book. Outside the US and Canada add \$10.00 for first book, \$5.00 for each additional book. All orders are processed upon receipt. If an order cannot be fulfilled within 90 days, payment will be refunded upon request. Prices are payable in US currency or its equivalent. Remember, your 30-day return privilege is always guaranteed. Pre-publication pricing: Unless otherwise stated, pre-pub prices are valid through the end of the third month following publication, and therefore are subject to change.

All € and £ prices are net prices subject to local VAT, e.g. in Germany 7% VAT for books and 19% VAT for electronic products. Pre-publication pricing: Unless otherwise stated, pre-pub prices are valid through the end of the third month following publication, and therefore are subject to change. All prices exclusive of carriage charges. Prices and other details are subject to change without notice. All errors and omissions excepted. Please consult springer.com for information on postage.

Contents

1 Introduction: Some Essential Attributes of Glassiness Regarding the Nature of Non-crystalline Solids	1
Hiroshi Suga	
2 Heat Capacity and Entropy Functions in Strong and Fragile Glass-Formers, Relative to Those of Disordering Crystalline Materials.....	21
C. Austen Angell	
3 Vibration Forms in the Vicinity of Glass Transition, Structural Changes and the Creation of Voids When Assuming the Role of Polarizability.....	41
Jaroslav Šesták, Bořivoj Hlaváček, Pavel Hubík, and Jiří J. Mareš	
4 Some Aspects of Vitrification, Amorphisation and Disordering and the Generated Extent of Nano-Crystallinity	59
Jaroslav Šesták, Carlos A. Queiroz, Jiří J. Mareš, and Miroslav Holeček	
5 Basic Role of Thermal Analysis in Polymer Physics.....	77
Adam L. Danch	
6 Phases of Amorphous, Crystalline, and Intermediate Order in Microphase and Nanophase Systems.....	93
Bernhard Wunderlich	
7 Thermal Portrayal of Phase Separation in Polymers Producing Nanophase Separated Materials.....	115
Ivan Krakovský and Yuko Ikeda	

8 Solid Forms of Pharmaceutical Molecules	129
Bohumil Kratochvíl	
9 Chalcogenide Glasses Selected as a Model System for Studying Thermal Properties	141
Zdeněk Černošek, Eva Černošková, and Jana Holubová	
10 Viscosity Measurements Applied to Chalcogenide Glass-Forming Systems	165
Petr Košťál, Jana Šhánělová, and Jiří Málek	
11 Thermal Properties and Related Structural Study of Oxide Glasses	179
Marek Liška and Mária Chromčíková	
12 Oxide Glass Structure, Non-bridging Oxygen and Feasible Magnetic Properties due to the Addition of Fe/Mn Oxides	199
Jaroslav Šesták, Marek Liška, and Pavel Hubík	
13 New Approach to Viscosity of Glasses	217
Isak Avramov	
14 Transport Constitutive Relations, Quantum Diffusion and Periodic Reactions	227
Jiří J. Mareš, Jaroslav Šesták, and Pavel Hubík	
15 In-Situ Investigation of the Fast Lattice Recovery during Electropulse Treatment of Heavily Cold Drawn Nanocrystalline Ni-Ti Wires	245
Petr Šittner, Jan Pilch, Benoit Malard, Remi Delville, and Caroline Curfs	
16 Emanation Thermal Analysis as a Method for Diffusion Structural Diagnostics of Zircon and Brannerite Minerals	261
Vladimír Balek, Iraida M. Bountseva, and Igor von Beckman	
17 Scanning Transitiometry and Its Application in Petroleum Industry and in Polymer and Food Science	271
Jean-Pierre E. Grolier	
18 Constrained States Occurring in Plants Cryo-Processing and the Role of Biological Glasses	291
Jiří Zámečník and Jaroslav Šesták	

19 Thermophysical Properties of Natural Glasses at the Extremes of the Thermal History Profile	311
Paul Thomas, Jaroslav Šesták, Klaus Heide, Ekkehard Füglein, and Peter Šimon	
20 Hotness Manifold, Phenomenological Temperature and Other Related Concepts of Thermal Physics.....	327
Jiří J. Mareš	
21 Historical Roots and Development of Thermal Analysis and Calorimetry.....	347
Jaroslav Šesták, Pavel Hubík, and Jiří J. Mareš	
Index	371

PROF. JAROSLAV ŠESTÁK, MENG., PHD., DSC.



Senior Scientist of the Institute of Physics, Academy of Sciences of the Czech Republic - specialised in thermodynamics (kinetics) and material science and engineering (particularly applied to variety of inorganic glasses), 287 papers in impact journals, over 2500 SCI citation responses, 15 books and book chapters, received honorary degree of Doctor Honoris Causa of the University of Pardubice (January 2010).

DR. JIRI J. MARES, PHD



Deputy Director of the Institute of Physics, Academy of Sciences of CR- specialised in condensed matter physics, deals with quantum properties of disordered systems and with fundamental problems of thermal physics and electrostatics, 123 papers in impact journals, over 230 citation responses, 3 books and book chapters.

DR. PAVEL HUBIK, PHD



Senior Scientist of the Institute of Physics, of Academy of Sciences of CR – deals with defects in semiconductors and with electron and thermal properties of solid state, 51 papers in impact journals, over 110 citation responses, 2 books and book chapters.

Preface

Early Research into Amorphous Semiconductors

Numerous aspects of physics and chemistry of non-crystalline solids and glassy state which are discussed in the present book can only hardly be prefaced without rude simplification. Therefore, let us make instead a short excursion to the prehistory of research into amorphous semiconductors, the topic on which the common epistemological features of the other subjects treated in this book may be demonstrated. It is a matter of fact that in everyday life we encounter more frequently noncrystalline than crystalline solids. We can even with some exaggeration say that in the Nature the perfect crystals are as rare as diamonds. In spite of that, the existence of the class of non-crystalline materials has been recognized only recently. One of the reasons for such a state of the art is probably the fact that the positivistic continuous model of matter dominated till the end of the nineteenth century and that the fundamental conjectures of atomism were too closely bound up with the idea of the regular ordering of atoms; early atomic theories accounting for the regular shape of snow flakes [1] and for the anisotropy of optical properties of transparent crystals [2], namely, exploited the idea that such a regularity is due to the closest filling of the space by identical hard polyhedrons or spheres, atoms. Denying atomic order in solids would thus undermine the strongest intuitive argument in favour of atomism, namely, that just the satisfaction of geometrical constraints between neighbouring atoms and their close packing accounts for actually observed regular shape of crystals. Interestingly enough, in the scientific disputations about the structure of matter, the existence of glass, for a long time known amorphous, i.e. "shapeless" material par excellence, was tacitly ignored. The serious attempts to treat the atomic structure of amorphous or glassy state are thus relatively recent, belonging to the first half of the twentieth century. The glass was at that time considered to be nothing but undercooled liquid i.e. a solid having essentially the atomic structure of original melt. Such a picture was an immediate consequence of phenomenological principle of continuity between liquid and solid state proposed by Frenkel [3], which was, among others, partially confirmed by means of X-ray analysis. Accordingly, namely, some characteristic structural patterns observed in the solid phase are, as a rule, observed in the liquid melt as well. From the broadening of X-ray diffraction patterns it was even possible to conclude that the glass comprises nanocrystals of typical size ~ 2 nm. (Today such a material would be classified rather as a nanocrystalline aggregate than glass.) Nevertheless, the phenomenological model provided neither the algorithm for the reconstruction of atomic lattice of glass nor the basis for the derivation of its physical properties from the structural ones. The first realistic model of glass lattice due to Zachariasen [4] was thus rather a result of physical reasoning than of a purely descriptive phenomenology. Crucial for the establishment of the model was the observation (from today's point of view not very exact!) that the mechanical properties of a glass, e.g. elastic bulk modulus or hardness, and of a corresponding crystal are similar. Consequently, the underlying building blocks have to have similar structural energies and must be matched together without further expense of energy. In order to satisfy these conditions it was suggested to identify the "underlying building blocks" with the nearest neighbourhood of each atom, the arrangement of which was only slightly changed with respect to that in a crystal. Cumulating small deviations of bond lengths ($\sim 1\%$) and tiny variations of bond angles ($\sim 1^\circ$) made it possible to match building blocks together and to construct a

random amorphous lattice without appreciable increase of structural energy. It can be shown that such a random lattice being locally almost identical with the periodic lattice of the corresponding crystal should reveal up to the second or the third coordination sphere practically the same radial distribution of atoms. For the following coordination spheres, however, huge differences are expected. The overall structural properties of amorphous solid may then be characterized quite simply by saying that the short-range order of atoms is preserved while the longrange order is absent. Evidently, this is quite a new concept of disorder, differing essentially from that encountered e.g. in gases. Being once established, the model of locally ordered homogeneous random network based on the absence of long-range order started to play more and more important role in modern solid state physics and chemistry.

By admitting new structural model, the problem of amorphous state was by no means definitely solved but just on the contrary. The researchers had to struggle with qualitatively new difficulties which appeared by computing the mechanical, optical and electronic properties of amorphous solids. As the semiconductors are materials which are known to be most sensitive to the changes of structural and chemical disorder, they may serve as a good example illustrating the fascinating development of solid state physics which followed. The quantum band model of solids as established in the 1930s was tailor-made for crystals having perfectly periodic lattice disturbed by only a small number of imperfections. Accordingly to Wilson's classification [5], the semiconductors were materials characterized by a "not very large" energy gap (~ 1 eV) in their electronic band structure. The very existence of the electronic band structure of solids was at that time treated as a direct consequence of periodicity of crystal lattice. Such an opinion was basically due to the establishment of famous Bloch's theorem [6] which enabled one to solve electronic structure of periodically arranged atoms even analytically (see e.g. Kronig-Penney model [7]). According to Bloch's theorem, namely, the interaction of an electron with the periodic crystal lattice may be replaced by its movement in a certain periodic potential. The solution of Schro" dinger equation in such a periodic field has a special form of harmonic wave with periodically modulated amplitude. In amorphous solids such a marvelous mathematical simplicity due to the perfect translational symmetry and long range order of crystals was lost forever and researchers have to learn how to do without Bloch's theorem. Moreover, the situation was further complicated by quite an astonishing experimental observation of Kolomiets [8] that chalcogenide glasses behave like intrinsic semiconductors which are essentially non-sensitive to the doping. Unexpectedly enough, theorists had to account for the surviving of the band model in the absence of lattice periodicity and for experimentalists quite a new field of research was opened, amorphous semiconductors. It should be stressed here that just these two circumstances had enormous impact on the further development of semiconductor science and technology.

The real boom of research into amorphous semiconductors was initialized by works of Ovshinski who reported about switching between a highly resistive and conductive state effected by an electric field and memory effects in chalcogenide glasses [9]. Immediately afterwards a plenty of new effects such as photodoping, reversible photostructural changes and optical memory effect having a huge application potential for imaging and electrophotography (e.g. Xerox process) were

discovered. Hand in hand with the promise of further applications steeply increased interest not only in chalcogenide glasses but also in other types of amorphous semiconductors (e.g. tetrahedrally bounded semiconductors) and in non-crystalline materials in general. Quite naturally there appeared a demand for a new scientific journal (Journal of Non-Crystalline Solids, 1st issue 1969) covering all these hot topics.

What were actually the main achievements in amorphous semiconductors during the decade from 1965 to 1975? First of all it was recognized that the band gap does exist also in amorphous semiconductors in spite of the absence of atomic longrange order. The band gap is, however, not empty but it contains an appreciable amount of localized states and its edges are no more sharp [10]. The position of the band gap edges and actual width of the band gap thus depends on the method of measurement. Transport band edges coincide with so called mobility edges where the mobility of carriers dramatically changes while the optical band gap (Tauc's optical gap [11, 12]) is determined by means of extrapolation of absorption curve. The localized states within the gap are, moreover, no passive entity. As a rule, at room and lower temperatures, they enable a special type of carrier transport via localized states, the so called hopping [13]. A new light on the character of localized states within the gap shed the path-breaking discovery of possibility of effective doping of amorphous silicon prepared by glow-discharge technique [14]. Passivation of localized gap states by hydrogen or other chemicals opened a new way to the tailoring of these materials. Besides the purely technological progress, the research into amorphous semiconductors stimulated development of qualitatively new methods of computing electronic structure of disordered solids and brought about changes in understanding to apparently closed topics [15]. We can thus claim that the research into amorphous semiconductors completely changed, within practically 1 decade, the gist of solid state physics as a whole. The concept of disorder became a corner stone of a lot of theories; the era of order was shared by the era where the concept of disorder dominated. And finally, in epistemological context provided the discovery of various aspects of disorder a valuable key to our understanding of a lot of natural systems and phenomena belonging not only to the scope of solid state physics and chemistry but also to biology, astrophysics and even to sociology.

May 2010

Jiří J. Mareš

Institute of Physics ASCR, v.v.i.
Prague, Czech Republic

Jan Tauc

Brown University
Providence, Rhode Island, USA

1. Kepler J (1987) *Strena seu de Nive Sexangula*. G. Tambach, Fracofurti ad Moenum (1611), German transl.: *Vom Sechseckigen Schnee*. Ostwald's Klassiker vol 273, Geest and Portig, Leipzig

2. Huyghens C (1903) *Traite' de la Lumie're*. Pierre van der Aa, Leide (1690), German transl.: *Abhandlung über das Licht*. W. Engelmann, Leipzig
3. Frenkel YaI (1945) *Kinetitsheskaya teoria zhidkosti*. Izd. AN SSSR, Moscow; English transl.: *Kinetic theory of liquids*. Clarendon, Oxford (1946)
4. Zachariasen WH (1932) The atomic arrangement in glass. *J Am Chem Soc* 54:3841–3851
5. Wilson AH (1931) The theory of electronic semi-conductors. *Proc R Soc London A* 133:458–491; *Proc R Soc London A* 134:277–287
6. Bloch F (1929) U' ber die Quantenmechanik der Elektronen in Kristallgittern. *Z Phys* 52:555–600
7. Kronig R de L, Penney WG (1931) Quantum mechanics of electrons in crystal lattices. *Proc RSoc London A* 130:499–513
8. Kolomiets BT (1964) Vitreous semiconductors (I), (II). *Phys Stat Sol* 7:359–372, 713–731; Original report in: *Proc IC on Semicon Phys Prague'60*, Czechoslovak Acad Sci (1961), p 884
9. Ovshinski SR (1968) Reversible electrical switching phenomena in disordered structures. *Phys Rev Lett* 21:1450–1453
10. Cohen MH, Fritzsche H, Ovshinsky SR (1969) Simple band model for amorphous semiconducting alloys. *Phys Rev Lett* 20:1065–1068
11. Tauc J, Grigorovici R, Vancu A (1966) Optical properties and electronic structure of amorphous germanium. *Phys Stat Sol* 15:627–637
12. Tauc J (ed) (1974) *Amorphous and liquid semiconductors*. Plenum, London
13. Mott NF, Davies EA (1971) *Electronic processes in non-crystalline materials*. Clarendon, Oxford
14. Spear WE, LeComber PG (1975) Substitutional doping of amorphous silicon. *Solid State Commun* 17:1193–1196
15. Shklovskii BI, Efros AL (1979) *Elektronnye svoistva legirovanykh poluprovodnikov* (Electronic Properties of Doped Semiconductors). Nauka, Moscow